



8XFINISHER'S EDGE LACQUER SANDING SEALER

TECHNICAL DATA SHEET

PRODUCT NUMBER

DESCRIPTION

B101-0803PLSM,FE732-001 -1,M102-0423	8xFINISHER'S EDGE LACQUER SANDING SEALER
---	---

PRODUCT DESCRIPTION:

This product is designed to match color and/or sheen on finished wood projects.

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	stearated nitrocellulose sanding sealer
Color	clear
Sheen	35-45
Viscosity	23-26 sec sig Zahn 1
WPG	6.566483100 lbs/gal
Solids by Volume	5.341716688 ±1%
Solids by Weight	8.436441700 ±1%
Flash Point	-76.000000000 °F
HMIS	H: 2, F: 4, R: 0, P: X
Coating VOC (g/l)	714.548402367 g/l
Coating VOC (Lb/Gal)	5.963218765 lbs/gal
Material VOC (g/l)	664.719965247 g/l
Material VOC (Lb/Gal)	5.547378541 lbs/gal
#VOC/#Solid	10.013725021 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.469364549
Spread Rate	85.680642766 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	Air dry @ 72 F, 35% relative humidity. To touch: 7 minutes; To handle: 15 minutes; To recoat: 30 minutes.
Oven Dry	User specific
Shelf-Life (Unopened)	36 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	Scuff sand with 320 grit as needed to smooth coating
PH	N/A

DIRECTIONS:

SHAKE WELL for at least one minute after ball rattles. Can temperature should be between 65° and 90°F. Hold can 12 to 14 inches away from surface to be coated. Press spray button firmly. Several thin coats work better than one heavy coat. Clean spray button after use by turning can upside down and pressing spray button until no more product comes out. FINISHING: Stain if desired. Seal with Sanding Sealer. Dry ½ hour before sanding. Apply topcoat. Dry ½ hour. Sand if needed. Apply second topcoat. REPAIR: If repair is rough, seal and sand. Feather topcoat evenly.

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.