



FINISHER'S CHOICE™ CLEAR FLAT

TECHNICAL DATA SHEET

PRODUCT NUMBER

M102-0542

DESCRIPTION

FINISHER'S CHOICE™ CLEAR FLAT

PRODUCT DESCRIPTION:

Mohawk Finisher's Choice™ Clears are high solids aerosol lacquers that eliminate the need to mix bulk finishes for your small refinishing and restoration jobs.

ADVANTAGES:

1. Higher solids, fast build
2. Outstanding atomization
3. Excellent blush resistance
4. Superior flow out

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Nitrocellulose lacquer
Color	Clear
Sheen	8° ± 2°; flat
Viscosity	N/A
WPG	6.621033239 lbs/gal
Solids by Volume	9.364674598 ±1%
Solids by Weight	14.831360705 ±1%
Flash Point	-76.000000000 °F
HMIS	H: 2, F: 4, R: 0, P: X
Coating VOC (g/l)	667.301619570 g/l
Coating VOC (Lb/Gal)	5.568923762 lbs/gal
Material VOC (g/l)	624.805672414 g/l
Material VOC (Lb/Gal)	5.214276384 lbs/gal
#VOC/#Solid	5.309911490 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.717402742
Spread Rate	150.208892808 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	To touch: 7 minutes, To handle: 15 minutes, To package: overnight
Oven Dry	N/A
Shelf-Life (Unopened)	36 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	Allow to dry 30 – 45 minutes between coats or until dry enough to scuff sand with 320 grit sandpaper
PH	N/A

DIRECTIONS:

Clean surface to be sprayed with Mohawk Wax Wash™ Remover. For best results, can temperature should be 65° - 90°. SHAKE WELL BEFORE USING for at least one minute after ball rattles to ensure color uniformity. Point opening of spray button toward object, holding can 12 to 14 inches away from surface to be coated. Press spray button firmly. Use steady, even strokes. Several thin coats give a better finish than one heavy coat. Allow coating to become tacky between coats. Clean spray button immediately by spraying with can upside down until no more product comes out. If clogged, remove spray button with a twisting motion and clean. Gently twist button onto can with opening turned away from you.

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.