



LEATHER REPAIR BASECOAT CHARCOAL GREY

TECHNICAL DATA SHEET

PRODUCT NUMBER	DESCRIPTION
M109-3016	LEATHER REPAIR BASECOAT CHARCOAL GREY

PRODUCT DESCRIPTION:

Mohawk Leather Repair Basecoats are heavily pigmented, opaque coatings used to hide the damage while starting the coloring process.

The Leather Repair Aerosols are used to color over damages on pigmented leather (also known as top coated) where there is color loss or the leather has been repaired. The aerosols are designed to enable you to match most of the leather furniture that is popular today. They are especially effective at repair

ADVANTAGES:

- Ø Opaque color – heavily pigmented
- Ø Hides off color repairs and provides basecoat color
- Ø Provides base color to build correct color match
- Ø Part of a complete system including toners, adjusters and topcoats.

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Pigmented Leather Lacquer
Color	Dark Grey
Sheen	10-20
Viscosity	25-30 Signature Zahn 1 @ 77F
WPG	6.517771606 lbs/gal
Solids by Volume	8.319513755 ±1%
Solids by Weight	14.193717067 ±1%
Flash Point	-76.000000000 °F
HMIS	H: 2, F: 4, R: 0, P: X
Coating VOC (g/l)	660.667802901 g/l
Coating VOC (Lb/Gal)	5.513563290 lbs/gal
Material VOC (g/l)	615.541895955 g/l
Material VOC (Lb/Gal)	5.136967527 lbs/gal
#VOC/#Solid	5.552793699 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.944762155
Spread Rate	133.445000630 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	none
Reducer	none
Retarder	none
AirDry	15 minutes
Oven Dry	not recommended
Shelf-Life (Unopened)	36 months
Pot-Life (Catalyzed)	n/a
Recoat Instruction	n/a

DIRECTIONS:

Opaque coating used to color and hide damage on leather. SHAKE WELL. Apply color nearest to leather color (but not darker) in thin coats (may take 2 - 4 coats) until the damage no longer shows through. Allow each coat 8 minutes dry time. Do not force dry. Use the other Mohawk leather aerosols; Leather Repair Toners, Leather Repair Color Adjusters and Leather/Vinyl Finish™ as needed to complete the repair. Clean spray button immediately

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.