



# WIPING WOOD STAIN VAN DYKE BROWN GAL

## TECHNICAL DATA SHEET

PRODUCT NUMBER	DESCRIPTION
M545-14786,M545-14787	WIPING WOOD STAIN VAN DYKE BROWN GAL

### PRODUCT DESCRIPTION:

Mohawk Wiping Wood™ Stains are semi-transparent, pigment based stains that are non-grain raising, fade resistant, easy to stir, soft settling formulas. Only 30 minutes drying time is needed before a lacquer sealer coat can be sprayed. Apply by spray, brush or cloth. Pigmented Wiping Stains are easier to control because there's less lapping. A dark color tone is easily lightened with Wood Stain Reducer S-15. This stain will never bleed through the finish. Virtually any Mohawk finish can be applied over Wiping Wood™ Stain; lacquer, shellac, varnish, polyurethane, acrylics and many others.

### ADVANTAGES:

1. Fade resistant, non-bleeding permanent colors.
2. Application by spray, rag or brush.
3. Ultra fine ground pigments for maximum color yield.
4. Seal coat may be applied over stain after 30 minutes of dry time.
5. HAP's compliant.

### PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Solvent base pigmented wiping stain
Color	Brown
Sheen	N/A
Viscosity	N/A
WPG	7.819773328 lbs/gal
Solids by Volume	7.547324362 ±1%
Solids by Weight	13.851813442 ±1%
Flash Point	106.000000000 °F
HMIS	H: 2, F: 2, R: 0, P: X
Coating VOC (g/l)	807.220094313 g/l
Coating VOC (Lb/Gal)	6.736602192 lbs/gal
Material VOC (g/l)	807.201528538 g/l
Material VOC (Lb/Gal)	6.736447253 lbs/gal
#VOC/#Solid	6.219222756 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.244336745
Spread Rate	121.059082766 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	M650-2507 S15 Stain Reducer; as needed for color
Retarder	N/A
AirDry	To touch; 5 min., To handle: 10 min., To topcoat: 30+
Oven Dry	User determined
Shelf-Life (Unopened)	36 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	N/A

**DIRECTIONS:**

STIR WELL BEFORE USING. Apply generously by wiping, brushing, or spraying. Allow to flash off momentarily, then use a clean absorbent cloth to remove excess. May be intermixed with other M545 Stains to create custom colors. Allow to dry (approximately 30 minutes) before sealing or topcoating.

*The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.*

*Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.*

*It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.*

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.