



# ROTTENSTONE 1 LB

## TECHNICAL DATA SHEET

### PRODUCT NUMBER

### DESCRIPTION

M720-1500,M720-1501,M72 0-1502 ROTTENSTONE 1 LB

### PRODUCT DESCRIPTION:

Rottenstone is a soft, mild abrasive that is used to polish lacquered or varnished surfaces to a high gloss finish. It can be used as an abrasive and in abrasive compositions. We recommend the use of Mohawk Rub Cut Oil or Behlen Paraffin Oil with Rottenstone.

### ADVANTAGES:

1. Mild abrasive
2. Produces a high gloss finish

### PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Abrasive
Color	Gray powder
Sheen	N/A
Viscosity	N/A
WPG	22.531959000 lbs/gal
Solids by Volume	100.000000000 ±1%
Solids by Weight	100.000000000 ±1%
Flash Point	999.000000000 °F
HMIS	H: 1, F: 0, R: 0, P: X
Coating VOC (g/l)	0.000000000 g/l
Coating VOC (Lb/Gal)	0.000000000 lbs/gal
Material VOC (g/l)	0.000000000 g/l
Material VOC (Lb/Gal)	0.000000000 lbs/gal
#VOC/#Solid	0.000000000 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.000000000
Spread Rate	1604.000000000 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	N/A
Reducer	N/A
Retarder	N/A
AirDry	N/A
Oven Dry	N/A
Shelf-Life (Unopened)	36 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	N/A
PH	N/A

### DIRECTIONS:

Sand to 1200 grit fineness or higher using Silicon Carbide Waterproof sandpaper with Rub Cut™ Oil, Paraffin Oil, Wool-Lube or water as a lubricant. Sprinkle a thin coat of Rottenstone and several drops of Mohawk Rub Cut™ or Behlen Paraffin Oil on the finish. Using a felt block or soft cloth, rub the mixture in long strokes with the grain until a uniform sheen is developed. Clean the surface with a soft rag.

*The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Industrial Coatings Group, Inc.; 3194 B Hickory Blvd, Hudson, NC 28638; Phone: 1-800-545-0047; Fax: 1-800-721-1545.*

*Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.*

*It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.*

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.