



ENDURAGREEN® FAST DRY SANDING SEALER

TECHNICAL DATA SHEET

PRODUCT NUMBER

DESCRIPTION

A28C3500BPR1,A28C3500 OHAW,A28C3500OHPD,A2 8C3500WP5
ENDURAGREEN® FAST DRY SANDING SEALER

PHYSICAL PROPERTIES AND SPECIFICATIONS

Technology	Waterborne Acrylic
Color	Milky white liquid, Clear when dry.
Sheen	40-60 Sheen at 3-4 Wet Mils Applied
Viscosity	19-23 Seconds #3 Signature Zahn Cup
WPG	8.64 lbs/gal
Solids by Volume	31.85 ±1%
Solids by Weight	34.14 ±1%
Flash Point	0.00 °F
HMIS	H: 2, F: 1, R: 0, P: X
Coating VOC (g/l)	160.70 g/l
Coating VOC (Lb/Gal)	1.34 lbs/gal
Material VOC (g/l)	62.40 g/l
Material VOC (Lb/Gal)	0.52 lbs/gal
#VOC/#Solid	0.18 lbs/lbs solid
VHAP Ratio (#VHAP/#Solid)	0.00
Spread Rate	510.92 sq. ft./gal @ 1.0 mil DFT (no loss)
Catalyst/Ratio	None
Reducer	Water, If Needed
Retarder	Propylene Glycol, If Needed - 2-3 oz per gallon
Air Dry	10-15 minutes dry to handle at room temperature. Recommend using at 65-85 degrees F, and between 25-60 % RH.
Oven Dry	10 minutes at 120F to sand
Shelf-Life (Unopened)	24 months
Pot-Life (Catalyzed)	N/A
Recoat Instruction	Air dry 20-30 minutes to sand. Topcoat with Enduragreen products.
PH	N/A

1 Freeze/thaw cycle. If product freezes, allow 48-72 hours to recover.
Maximum dry film thickness for total system not to exceed 4 dry mils

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. SDS and CPDS sheets are available upon request. Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data. The following definitions are being utilized for HAP content: "HAPS-Compliant": < or = .8 lb. HAPS/Lb. Solids; "Low-HAPS": <.5 Lb. HAPS/Lb. Solids; "Ultra-Low-HAPS": <.2 Lb. HAPS/Lb. Solids; "HAPS-Free": <0.00 Lb. HAPS/Lb. Solids. HAP content is based upon the presence of HAP compounds utilizing limits as defined in 29 CFR 1910.1200. Manufacturer assumes no liability for use of this information which is intended to serve as a general guide.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Finishworks™, Division of RPM Industrial Coatings Group, Inc. All rights reserved.