



ENDURAGREEN W/B CONVERSION VARNISH SEMI-GLOSS 60 SHEEN GAL

TECHNICAL DATA SHEET

| PRODUCT NUMBER | DESCRIPTION |
|----------------|---|
| M641-21607 | ENDURAGREEN W/B CONVERSION VARNISH SEMI-GLOSS 60 SHEEN GAL |

PRODUCT DESCRIPTION:

N/A

PHYSICAL PROPERTIES AND SPECIFICATIONS

| | |
|---------------------------|---|
| Technology | Waterborne Urethane/Acrylic |
| Color | CLEAR |
| Sheen | 60 +/-2 @ 5 Wet Milis Applied |
| Viscosity | 28 +/- 2 #4 Signature Zahn Cup |
| WPG | 8.587664547 lbs/gal |
| Solids by Volume | 27.215201544 ±1% |
| Solids by Weight | 29.602849744 ±1% |
| Flash Point | 200.000000000 °F |
| HMIS | H: 2, F: 1, R: 0, P: X |
| Coating VOC (g/l) | 229.130622257 g/l |
| Coating VOC (Lb/Gal) | 1.912187387 lbs/gal |
| Material VOC (g/l) | 84.096666164 g/l |
| Material VOC (Lb/Gal) | 0.701823195 lbs/gal |
| #VOC/#Solid | 0.276069943 lbs/lbs solid |
| VHAP Ratio (#VHAP/#Solid) | 0.006594235 |
| Spread Rate | 436.530069874 sq. ft./gal @ 1.0 mil DFT (no loss) |
| Catalyst/Ratio | A59C8700 Catalyst -2.5 oz/gallon for enhanced chemical and water resistance |
| Reducer | Ready To Spray - May Add Small Amount Water If Desired |
| Retarder | Propylene Glycol if Needed For Longer Open Time - Use 1-3 Oz Per Gallon to prevent drying on tips |
| AirDry | Apply 1 Coat Over 1 or 2 Coats A29C4000 Sealer. Sand Sealer With 280, then 320 or 400 Grit. |
| Oven Dry | 20 MINUTE FLASH -25 @ 120F TO HANDLE |
| Shelf-Life (Unopened) | 12 months |
| Pot-Life (Catalyzed) | 24 Hours. |
| Recoat Instruction | AIR DRY 1.5 HOURS MINIMUM TO RECOAT, SCUFF WITH 380 OR 400 GRIT PRIOR TO RECOAT. |
| PH | 8.3 |

The data on this sheet are calculated values (as formulated) and will not represent exact values for every product. For Safety and Other Precautions, read the SDS before using the product. SDS are available upon request. If Safety Data Sheet is required, contact: Mohawk Finishing Products, a Division of RPM Wood Finishes Group, Inc.; P.O. Box 22000 Hickory, NC 28603; Phone: 1-800-545-0047; Fax: 1-800-721-1545.

Drying times and viscosities reported are as tested under laboratory conditions (77°F (25°C)) with relative humidity of approximately 45%. Changes in temperature and humidity will affect product data.

It is the user's responsibility to verify product compliance with all applicable regulations or permits before proceeding with use. Always pretest any finishing products to verify suitability to the desired use before proceeding with any application. Manufacturer makes no warranties, express or implied, including (but not limited to) warranties of merchantability and fitness for particular purposes. Manufacturer will not be liable for any incidental, consequential or special damages or losses derived, directly or indirectly, from or as a consequence of purchaser's use of this product.

TDS. Mohawk Finishing Products, Division of RPM Wood Finishes Group, Inc. All rights reserved.