

Mohawk Finishing Products

Division of RPM Wood Finishes Group, Inc.

Product Data Sheet

DuraCoat™ II Post-Catalyzed White

M612-3680 (Gloss), M612-3660 (Semi-gloss), M612-3640 (Satin), M612-3620 (Matte)
Available in 1 gallon (125 fluid ounce) and 5 gallon (625 fluid ounce) containers.

Product Description: DuraCoat™ II Post-Catalyzed White is 275 VOC compliant, high quality finish that must be catalyzed with DuraCoat™ II Catalyst (M612-301) before use, which helps to build resistance properties into the finish. The finish reaches maximum characteristics after 30 days and has a 6 month shelf life after catalyzing.

Advantages:

1. Extended shelf life
2. 275 VOC compliant.
3. HAP's and Rule 66 compliant
4. Excellent toughness, resistance and stability
5. Ready to spray, no reduction required

Characteristics:

Weight per gallon: 8.41* lbs/gal

Solids % (wt): 31.84*

Solids % (vol): 20.79*

Package viscosity: 12-14 seconds, # 4 Ford cup

Dry time: Air dry @ 72 F, 35% relative humidity

To touch: 7 minutes

To handle: 15 minutes

To sand and recoat: 30-45 minutes

To rubout or package: 24 hours

VOC's (coating): 2.29*lbs/gal (275 g/l max.)

VOC's (material): .71*lbs/gal (84.68g/l)

HMIS: Health – 2, Flammability – 3, Reactivity – 0, Personal Protection - X

VHAP's: 0.044* lbs VHAP's/lb solids

Spread rate: 335 sq ft @ 1 dry mil

Sheen: Gloss: ≥ 80, Semi-gloss: 60, Satin: 40, Matte: 20

Shelf Life: 6 months after addition of catalyst.

(Contains nitrocellulose resins, which tend to amber in color over time but does not affect coating performance)

*Varies between sheens.

All values theoretical; not intended to be exact QC specifications.

Directions: Add 1 bottle of the pre-measured (packaged in 3.2 oz./single gallon and 16 oz./5-gal pails bottles) DuraCoat™ II Catalyst (M612-301) to catalyze the entire container of DuraCoat™ II Post-Catalyzed White Lacquer. Stir material while adding catalyst and continue to stir until thoroughly mixed. Material is now ready for spraying. Seal with E-Z Vinyl® White Sealer (M612-106). Do not use a sterated, nitrocellulose sanding sealer as a sealer with this product. Sterated, nitrocellulose sanding sealers may cause acid blooming.

Apply DuraCoat™ II Post-Catalyzed White Lacquer in light, even coats of no more than 3-4 wet mils. If needed, apply the second coat in a light, even coat of no more than 3-4 wet mils, allow to dry. Sand with 320 grit sandpaper. All Mohawk 275 VOC formulations are high solids products, which build very quickly. Total film build of the entire system, including topcoats, should not exceed 4 dry mils. Excessive build may lead to poor adhesion, cracking or cold check problems. Remove sanding dust before topcoat application. Mohawk Retarder for Low VOC Coatings (M612-1056) is recommended if a flow enhancer is needed.

NOTES: The entire container of DuraCoat™ II Post-Catalyzed White Lacquer must be catalyzed at once. Do not catalyze partial amounts. Attempting to catalyze partial amounts may result in poor performance of the product. DuraCoat™ II Post-Catalyzed White Lacquer is manufactured at spray viscosity. If further reduction or retarding of the coating is required, use Mohawk Retarder for Low VOC Coatings (M612-1056). Stainless steel spray equipment is recommended to avoid iron contamination (discoloration). Total dry film should not exceed 4 mils. All products should be stirred properly before being used and also continuously agitated while in use to insure product consistency from start to finish. Filtering at every opportunity is suggested. The system should be pre-tested on the wood to be finished under application conditions. Mixing with other products or finish systems is not recommended. Mohawk Finishing Products will not be held liable for finish failure resulting from mixing products or systems. This product is formulated for interior applications and is not recommended or tested for exterior applications.

Safety and Other Precautions: Read MSDS for precautions before using product.

MSDS: If Material Safety Data Sheet is required, contact:

Mohawk Finishing Products

Division of RPM Wood Finishes Group, Inc.

P.O. Box 22000

Phone: 1-800-545-0047

Hickory, NC 28603

Fax: 1-800-721-1545

Mohawk 275 VOC Coatings

Tip Sheet

Viscosity is typically much lower or thinner in 275 VOC coatings because they have to be in order to achieve proper flow out of the coating.

Agitation is needed to thoroughly mix flattening agents and pigments in opaque colors into all coatings. Periodic agitation is always recommended for most clear and opaque coatings. However it is particularly important with 275 VOC coatings because 275 VOC products tend to settle faster due to the lower viscosity, which can allow flattening agents and pigments to fall out of suspension much faster than in higher VOC formulations.

For best results, always agitate or stir 275 VOC products more frequently in order to maintain a consistent sheen or color. A good habit to get into is to stir the 275 VOC products at least every 10 minutes.

Application of 275 VOC coatings does have a few new things to remember.

1. Stir/Agitate 275 VOC coatings frequently.
2. Lighter coats work better than heavy wet coats. Do not try to level a coat by applying it too heavy. Excessive build could occur.

3. Lowering your air or fluid pressure will reduce the risk of the product going on dry.
4. Hold the gun a little closer to the substrate when applying to reduce the risk of applying too dry.

Build can be deceiving with a 275 VOC coating. In fact, it is very easy to exceed the maximum build of 4 dry mils.

To reduce this risk, try to keep the four coat rule. **DO NOT APPLY MORE THAN 4 TOTAL COATS INCLUDING SEALERS OR PRIMERS.**

275 VOC coatings may be lower in viscosity but they remain high solids coatings. Exceeding the 4 coat rule can increase the chances of excessive build, which can result in cracking or other finish failures.

Mohawk 275 VOC Products include:

M612-2500 series Clear WW Lacquer

M612-800 E-Z Vinyl® Sealer

M612-3400 series Duracoat™ II Post-Catalyzed Lacquer

M612-3600 series Duracoat™ II Post-Catalyzed White Lacquer

M612-2800 series Ultra™ Clear Conversion Varnish (Post Catalyzed)

M612-2700 series Ultra™ White Conversion Varnish (Post Catalyzed)

M612-106 & M612-306 E-Z Vinyl® Colored Sealer